TRIPKO

TRIPKO CONSULTING LTD.

VATHI AVLIDAS, 341 00 CHALKIDA, GREECE TEL.: +30 213 018 4675

FORMS OF SUPPLY

LAUROCRYL B-700

LAUROCRYL[®] B-700: 60% in toluene

TYPE AND USE

LAUROCRYL B-700 is a thermoplastic acrylic resin, suitable for the production of road-marking paints.

SOLUBILITY

White spirit:	insoluble
Aromatic hydrocarbons:	complete
Esters, ketones:	complete
Alcohols:	insoluble

TECHNICAL CHARACTERISTICS

Non-volatile content (ELOT EN ISO 3251)	. 60% ± 2%
Viscosity, 60% in toluene	
25°C (ELOT EN ISO 2884) mPa.s	2000 - 5000
Acid value (ELOT EN ISO 2114 on n.v.)	max. 18
Colour,50% nv	
Gardner colour scale (ELOT EN ISO 4630)	max. 1
OTHER CHARACTERISTICS (informative)	
Flash point	approx. 4°C

The information contained herein is provided in good faith and is to the best of our knowledge accurate. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety and additional information please refer to the Material Safety Data Sheet as well as to other informative documents accompanying the product.

LAUROCRYL B-700 en Version 1.1