## **TRIPKO**

TRIPKO CONSULTING LTD.

VATHI AVLIDAS, 341 00 CHALKIDA, GREECE TEL.: +30 213 018 4675

### **FORMS OF SUPPLY**

LAUROCRYL® B-711: 60% in xylene

# **LAUROCRYL B-711**

#### **TYPE AND USE**

LAUROCRYL B-711 is a thermoplastic acrylic resin, suitable for the production of metal coatings, spray paints as well as for road-marking paints.

#### **SOLUBILITY**

White spirit:	insoluble
Aromatic hydrocarbons:	complete
Esters, ketones:	complete
Alcohols:	insoluble

TECHNICAL CHARACTERISTICS	
Non-volatile content (ELOT EN ISO 3251)	
Viscosity, delivery form	
25°C (ELOT EN ISO 2884) mPa.s	3000 – 9000
Acid value (ELOT EN ISO 2114 on n.v.)	max. 18
Colour,50% nv	
Gardner colour scale (ELOT EN ISO 4630)	max. 2
OTHER CHARACTERISTICS (informative)	
Flash point	approx. 25°C

The information contained herein is provided in good faith and is to the best of our knowledge accurate. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety and additional information please refer to the Material Safety Data Sheet as well as to other informative documents accompanying the product.

LAUROCRYL B-711 en Version 1.0