TRIPKO CONSULTING LTD.

FORMS OF SUPPLY

LAUROKYD® F-1700: 100% non - volatile

LAUROKYD F-1700

5000 – 8000

...... max. 12

TYPE AND USE

LAUROKYD F-1700 is a high solids long — oil alkyd resin, specially designed for decorative coatings complying to the European Directive 42/2004EC for the reduction of the VOC in coatings. With the use of LAUROKYD F-1700 and low — odour solvents, one can produce odourless enamels for indoor use.

PRINCIPAL PROPERTIES

Very good yellowing resistance, good balance between touch drying and through drying, without wrinkling tendency, good rheological properties.

High gloss and gloss retention and high weathering resistance.

COMPOSITION

Viscosity, delivery form

Colour,50% nv

25°C (ELOT EN ISO 2884) mPa.s

Acid value (ELOT EN ISO 3682 on n.v.)

Gardner colour scale (ELOT EN ISO 4630)

OTHER CHARACTERISTICS (informative)

Type of oil: specially selected Fatty Acids	
Oil length: approx. 70%	
Phthalic anhydride: approx. 15%	
Type of polyol: Mixed polyols	
SOLUBILITY	
White spirit: complete	
Aromatic hydrocarbons: complete	
Esters, ketones: complete	
Alcohols: insoluble	
TECHNICAL CHARACTERISTICS	
Non-volatile content (ELOT EN ISO 3251)	NA

The information contained herein is provided in good faith and is to the best of our knowledge accurate. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety and additional information please refer to the

Material Safety Data Sheet as well as to other informative documents accompanying the product.

LAUROKYD F-1700 en Version 1.0