

TRIPKO CONSULTING LTD

ACRYLIC RESINS, SOLVENT BASED (THERMOPLASTIC)

LAUROCRYL®	NON-VOLATILE %	SOLVENT	VISCOSITY 25° C dPa.s delivery form	ACID VALUE	APPLICATIONS
B-505	60	Toluene	30 – 90	max 7	Wall primers, stone varnishes
B-516	60	Xylene	30 – 90	max 7	Spray paints, wall primers, stone varnishes
B-700	60	Toluene	20 – 50	max 18	Road-marking paints
B-711	60	Xylene	30 - 90	max 18	Spray paints, road-marking paints
B-731	60	Butyl acetate	40 - 90	max 18	Road-marking paints, spray paints
B-800	60	White spirit*	80 – 120	max 5	Wall primers, wall paints
B-900	60	Shellsol D40	45 – 85	max 5	Wall primers, wall paints

* Aromatic content W.S. = 16 – 18%