

ALKYD RESINS, SHORT OIL

LAUROKYD®	OIL CONTENT %	OIL TYPE *	NON-VOLATILE CONTENT %	SOLVENT *	VISCOSITY 25º C DELIVERY FORM dPa.s	ACID VALUE	COLOUR GARDNER	APPLICATIONS								
								FAST AIR-DRYING INDUSTRIAL ENAMELS	STOVING ENAMELS	ANTICORROSIVE PAINTS & UNDERCOATS	N/C LACQUERS & FILLERS	2 P-PUR SEALERS & SURFACERS	2 P-PUR FINISHES	AUTOMOTIVE STOVING PRIMERS	AUTOMOTIVE REPAIR ENAMELS	ACID CURING
A-306	30	SP	60	X	40-60'' D4/40%	max 15	max 6					●	●			
A-386	38	F.A./ CASTOR	60	X	25-50'' D4/40%	15 – 22	max 6					●	●			
A-408	40	DCO	60	X	20 – 35	16-22	max 6	○	●		●	○	●	●	●	●
A-450	45	CASTOR OIL	60	X	5 – 15	15 – 25	max 4		●		●		○	●		●
F-320	32	F.A.	60	X	45 – 70	max 12	max 6	●	○	●	○				●	
F-322	32	F.A.	60	X	140 – 220	max 12	max 7	●	○	●	○				●	
F-396	40	SP	60	X	50 – 80	max 12	max 6	●	○	●	○				●	

F.A.: FATTY ACIDS

W.S.: WHITE SPIRIT

MP: METHOXY PROPANOL

S: SOYA BEAN OIL

X: XYLENE

SP: SPECIAL OILS/ FATTY ACIDS

D40: SHELLSOL D40 (SHELL)

T: TOLUENE