

LAUROCRYL B-900

FORMS OF SUPPLY

LAUROCRYL[®] B-900: 60% solids in isoparaffinic solvent (e.g. Shellshol D 40*)

*ShellSol = TM Shell Chemicals

TYPE AND USE

Modified thermoplastic styrene-acrylic resin. Binder for cement facing substrates, low viscosity primers and wall paints. Also suitable for stone varnishes in aliphatic solvent.

PRINCIPAL PROPERTIES

Very good adhesion to cementitious surfaces.

Good permanent flexibility.

Excellent insulating properties.

SOLUBILITY

Isoparaffinic solvents complete

Aromatic hydrocarbonscomplete

Esters, ketones complete

Alcohols insoluble

TECHNICAL CHARACTERISTICS

Non-volatile content (ELOT EN ISO 3251) 60±1%

Viscosity, 60% in isoparaffinic solvent

25°C (ELOT EN ISO 2884) mPa.s 4.500 - 8.500

Acid value (ELOT EN ISO 3682 on n.v.) 5 max

Colour, 50% nv

Gardner colour scale (ELOT EN ISO 4630) 2 max

OTHER CHARACTERISTICS (informative)

Flash point approx. 40°C

The information contained herein is provided in good faith and is to the best of our knowledge accurate. Therefore, the buyer is advised to determine the suitability of this product for the intended use. We retain the right to make any changes according to technological progress or further developments. For safety and additional information please refer to the Material Safety Data Sheet as well as to other informative documents accompanying the product.

LAUROCRYL B-900 en
Version 2.0